

Property	Units	LHM+	Pentosin CHF 11S	ATF+3	Texaco MIL-H-5606(G)	Lubriplate Low Pour	Lubriplate -70
Colour	-	Green	Green	Red	Red	Clear/Amber	Clear/Amber
Density at 15C	Kg/l	0.830	0.825	0.825	0.86	?	?
Viscosity at -40C	cSt	<1200	<1100	1500	?	?	?
Viscosity at -20C	cSt	?	230	?	?	?	?
Viscosity at 0C	cSt	?	?	?	?	?	?
Viscosity at 20C	cSt	?	?	?	?	?	?
Viscosity at 40C	cSt	18	18.6	36.8	13.5	25	16
Viscosity at 50C	cSt	?	?	?	?	?	?
Viscosity at 100C	cSt	6.3	>6	7.65	5.0	7	6
Viscosity index	-	355	320	185	372	210	340
Pour point	Deg C	-62	<-62	-45	-80	-57	-57
Boiling point	Deg C	255	?	?	?	?	?
Flash point	Deg C	135	?	?	?	157	93